

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:

Naoya Amino et al.

Application No.: 10/590,800

Confirmation No.: 2201

Filed: August 25, 2006

Art Unit: 1796

For: Rubber Composition
for Tire Tread

Examiner: EA SHOO, Mark

DECLARATION UNDER 37 C.F.R. §1.132

Commissioner for Patents

P.O. Box 1450

Alexandria, VA 22313-1450

Dear Sir:

I, Naoya Amino, a citizen of Japan, residing at 2-1,
Oiwake, Hiratsuka, Kanagawa, Japan respectively, sincerely
and solemnly declare:

1. I am by profession a research chemist and that I
graduated from Kyoto University, Faculty of Engineering and
Department of Polymer Science, on March, 1993. Since

April, 1993, I have been employed by THE YOKOHAMA RUBBER Co. Ltd. and have been engaged in research, as a researcher, especially developments of rubber compositions for pneumatic tires, etc. in the Development Center of The YOKOHAMA RUBBER CO. LTD.

2. The following Experiments were carried out by me and/or under my direction and/supervision.

3. Experiments 1 and 2

The ingredients shown in Table A below, except for the vulcanization accelerator and sulfur were mixed in 1.7 liter Banbury mixer at 160°C for 5 minutes, then an open roll was used to add and mix the vulcanization accelerator and sulfur to obtain a rubber composition.

The resultant rubber compositions shown in Table A were used, according to a conventional method, to fabricate treads for 195/65R15 size tires and determined the braking distance from an initial speed of 100 km/h on an asphalt road surface. The results are shown in Table A, as indexed to Examples III-2 and III-5, both in the present specification, as 100. The larger the value, the shorter the braking distance and the better.

The ingredients used in Table A are as follows.

SBR-1: Nipol 9528R (see Note 1) of Table III-2 of the
present specification) ($T_g = -35^{\circ}\text{C}$)

SBR-3: Nipol/721 (made by Nippon Zeon), containing
27.2 wt% extended oil, $T_g = -28^{\circ}\text{C}$

Rubber gel-1: See Note 3) of Table III-2 on page 35 of the
present specification ($T_g = -31^{\circ}\text{C}$)

Rubber gel-A: See Note 2) of Table III-3 on page 36 of the
present specification ($T_g = -28^{\circ}\text{C}$)

Carbon black: See Note 5) of Table III-2 above

Antioxidant: See Note 8) of Table III-2 above

Zinc White: See Note 9) of Table III-2 above

Stearic acid: See Note 10) of Table III-2 above

Process oil: See Note 11) of Table III-2 above. As is
clear from Table A, the oil content was the
same in all Experiment 1 and 2 and
Examples III-2 and III-5 due to the amount of
the extended oil in the rubber.

Vulcanization accelerator: See Note 12) of Table III-2
above

Sulfur: See Note 13) of Table III-2 above.

4. As is clear from the results shown in Table A below, wherein the additional Experiments 1 and 2 using SBR-3 having Tg of -28°C, instead of Rubber Gel-1 having a Tg of -31°C in Example III-2 of the present application and Rubber Gel-A having a Tg of -28°C in Example III-5 of the present application were used, respectively, the desired results cannot be obtained when the two types of the aromatic vinyl-conjugated diene copolymer rubbers having the Tg difference within 10 degree are used. Thus, the use of the specified conjugated diene-based rubber gel is essential for the present invention.

Table A

Formulation (parts by weight)	Experiment 1 ^{*3} Example III-2 ^{*1}	Experiment 2 ^{*3} Example III-5 ^{*2}
SRB-1	96.25(26.25) ^{*4}	110(30) ^{*4}
SRB-3	41.25(11.25) ^{*4}	27.5(7.5) ^{*4}
Rubber gel-1	-	-
Rubber gel-A	30	-
Carbon black	-	20
Antioxidant	80	80
Zinc White	1	1
Stearic acid	3	3
Process oil	1	1
Vulcanization accelerator	11.25	7.5
Sulfur	1.5	1.5
	2	2
Wet braking performance (index)	92	96
	100	100

*1: See Table III-2 on page 35 of the present specification

*2: See Table III-3 on page 36 of the present specification

*3: Additional Experiment

*4: Oil content (wt. part)

CONCLUSION

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.



Naoya Amino

Date: this 31st day of July , 2008